

ABSTRACT OF THE DISCLOSURE

A method is provided, the method including forming a gate dielectric above a surface of the substrate and forming a doped-poly gate structure above the gate dielectric, the doped-poly gate structure having an edge region. The method also includes forming a
5 dopant-depleted-poly region in the edge region of the doped-poly gate structure adjacent the gate dielectric.